

# CERAFIN

## PROTECTIVE BARRIER COATING

### FEATURES & BENEFITS:

- Graffiti Resistant
- Excellent Corrosion Resistance
- Can Be Applied to New or Previously Painted Surfaces
- Single Coat Application
- Non-Sacrificial
- UV Resistant
- Easy to Clean Graffiti from Coated Surfaces
- Excellent Adhesion
- Excellent Gloss Retention
- Extremely Resilient
- Chemical Resistant

### APPLICATION USES:

- Walls
- Fiber Reinforced Plastic (FRP)
- Drywall
- Cinder Block
- Masonary
- Concrete
- Steel
- EIFS (Exterior Insulation Finishing System)
- Interior and Exterior Surfaces



Green Chemistry  
Low VOC



THE SHIELD  
to your surface. 

GOES ON  
**STRONG.**  
stays on long.

FOOLPROOF  
*graffiti*  
PROOFING

OFFICIALLY  
NON-SACRIFICIAL

TO PROTECT  
 PRESERVE

KEEP WRITING  
OFF THE WALL

ONE COAT   
and you're covered.

PROTECTIVE  
**POWER**

 in a pail. 

OFF THE WALL  
cleanability.



**SIMIRON**<sup>TM</sup>

INNOVATIVE PROTECTIVE COATINGS

# The BARRIER IN A BUCKET.

# CERAFIN

## PROTECTIVE BARRIER COATING



### INTERIOR & EXTERIOR USES:

- Bridge Abutments
- Transit Stations
- Commercial Buildings
- Overpasses
- Schools
- New Construction
- Railcars

### PERFORMANCE DATA:

Adhesion	ASTM D-6677	Passes; Rating 8
QUV	4000 Hours	Passes
Abrasion Resistance	ASTM D4060	25 mg loss
	CS17 Wheel, 1000 cycles, 1Kg load	
Gloss Retention	4000 QUV hours	96%
Hardness, Shore D	ASTM 2240	75
Graffiti Resistance	24 hours	Excellent
Graffiti Resistance	4000 QUV hours	Excellent
Graffiti Resistance	ASTM D6578	9.14

### TECHNICAL DATA:

Finish	Clear Gloss
Components	2
Volume Solids	80%
Weight Solids	83%
VOC	<50 g/L

(EPA Rule 40 CFR 59)

Coverage	300-400 sq/ft (28-37m <sup>2</sup> ) per kit
Dry Film Thickness	3-4 mils (75-100 microns)
Drying Schedule	@ 77°F (25°C) 50% relative humidity
	To Touch 4-6 hours
	Full Cure 24 hours

Shelf Life (Unopened): 12 months from date of manufacture

#### Graffiti Removal

Most graffiti can be cleaned off by power washing the surface with a 1200-1500-psi pressure washer and a 25° tip or clean with Cerafin Graffiti Remover, mild detergents or solvents such as IPA, Acetone or Xylene.