

800CF

— EPOXY CRACK FILLER —

SIMIRON 800CF is an easy-to-use two-component, 100% solids epoxy concrete crack filler. This formula is thickened for ease of use to repair cracks, holes, and damaged concrete on vertical or horizontal surfaces.



FEATURES & BENEFITS:

- Seamless Repairs
- Easy-to-Mix 1:1 Ratio
- Excellent Adhesion
- Sag-resistant
- 100% Solids Formula
- Virtually Odor-free
- VOC Compliant

RECOMMENDED USES:

- Concrete
- Warehouses
- Retail
- Industrial
- Commercial
- Garages
- Residential Homes



800CF

EPOXY CRACK FILLER

SIMIRON 800CF is an easy-to-use two-component, 100% solids epoxy concrete crack filler. This formula is thickened for ease of use to repair cracks, holes, and damaged concrete on vertical or horizontal surfaces.



PRODUCT INFORMATION

PRODUCT NAME	SIZE	COLOR/FINISH	ITEM NUMBER
Complete Kit	2-Quart	Haze Gray	50001048
Complete Kit	1-Gallon	Haze Gray	40002862
Complete Kit	2-Gallon	Haze Gray	50001047

TECHNICAL DATA

PHYSICAL DATA

Components	2 (Base & Activator)
Color	Haze Gray
Solids Content	100%
Solids Content	2 Base: 1 Activator
Mix Ratio (by volume)	Chemical reaction between components
Gel Time 100 Gram mass @ 72°F (22°C)	2 - 3 minutes
VOC (EPA Method 24)	11 g/L

THEORETICAL COVERAGE

.13 cu. ft. per gallon or 1,228 lineal ft. of 1/8" x 1/8" cracks

CURE TIMES

CURE TIMES	STANDARD
Work Time	35 - 45 minutes
Tack Free	8 - 10 hours
Light Foot Traffic	24 hours
Full Cure	5 days
Recoat	Immediately

PHYSICAL PERFORMANCE PROPERTIES

PHYSICAL PROPERTIES	TEST METHOD	RESULTS
Adhesion to Concrete	ASTM D4541	350 psi (100% Concrete Failure)
Compressive Strength	ASTM D695	8,710 psi
Elongation	ASTM D638	2.5%
Hardness (24 hour Shore D)	ASTM D2240	65
Heat Deflection	ASTM D648	138 F (59 C)
Impact Resistance (Gardner)	ASTM D2794	50 in-lbs.
Tensile Strength	ASTM D638	6,256 psi

SIMIRON COLOR SELECTION

HAZE GRAY



3000 Research Drive
Rochester Hills, MI 48309-3580
866.515.8775 SIMIRON.COM



SCAN FOR MORE INFO