




SIMFLAKE SB SYSTEM GUIDE



TOPCOAT: POLYASPARTIC HS SLOW CURE

BASECOAT/BROADCAST: 1100SL 100% SOLIDS EPOXY, PIGMENTED & DECORATIVE CHIP

PRIMER: 1000HS 100% SOLIDS EPOXY PRIMER, CLEAR

PREPARED SUBSTRATE: CSP 3+

NOTE: PLEASE READ AND REVIEW THESE INSTRUCTIONS PRIOR TO INSTALLATION OF THE COATING SYSTEM.

OTHER SIMIRON PRODUCTS MAY BE USED AS ALTERNATIVE PARTS OF THIS SYSTEM. CONTACT SIMIRON TECHNICAL SUPPORT AT CUSTOMERSERVICE@SIMIRON.COM OR 866-515-8775.

DESCRIPTION

SIMFLAKE SB is a versatile, single-broadcast floor system that utilizes Simiron Decorative Chip to achieve easy to maintain, long-lasting results. This three-layer system offers 12 standard blends. The featured system has a gloss finish, but optional satin and non-skid texture is available. SIMFLAKE SB consists of a primer, basecoat, 1/8" vinyl chip broadcast, and topcoat. The base system will produce an average nominal thickness of 60 mils.

PRODUCT INFORMATION

PRODUCT NAME	SIZE	COLOR/FINISH	ITEM NUMBER
1000HS 100% Solids Epoxy Primer	1.5-Gallon Kit	Clear / Gloss	40008895
1100SL 100% Solids Self-Leveling Epoxy, Part A Base	2-Gallon	Clear / Gloss	40004156
1100SL 100% Solids Self-Leveling Epoxy, Part B Activator	1-Gallon	Clear / Gloss	40004155
Decorative Chip	50 lb. Box	33 Available Blends	
Polyaspartic HS Slow Cure	2-Gallon Kit	Clear / Gloss	40008919

1100SL Clear can be pigmented with Simiron E-Tints in the following colors: Haze Gray, Light Gray, Deck Gray, Sandstone, White, Black, & Tile Red.

COVERAGE RATES

PRODUCT NAME	WET FILM THICKNESS	DRY FILM THICKNESS	COVERAGE RATE
1000HS 100% Solids Epoxy Primer	3 - 8 mils	3 - 8 mils	200 - 533 sq. ft./gal.
1100SL 100% Solids Self-Leveling Epoxy	8 - 12 mils	8 - 12 mils	134 - 200 sq. ft./gal.
Decorative Chip	N/A	N/A	6 sq. ft./lb. or 300 sq. ft. per 50 lb. box
Polyaspartic HS Slow Cure	10 - 16 mils	9 - 14 mils	100 - 160 sq. ft./gal.

PHYSICAL PROPERTIES

TEST NAME	TEST METHOD	RESULT
Adhesion to Concrete	ASTM D4541	> 400 PSI (100% Concrete Failure)
Coefficient of Friction (Wet SCOF)	ANSI / NFSI B101.1	.55
Compressive Strength	ASTM D695	11,600 psi
Elongation	ASTM D2370	5 – 10%
Flammability		Self-Extinguishing on Concrete
Flexibility 1/8" Mandrel	ASTM D522	Passes/No Cracking
Flexural Strength	ASTMD790	12,800 psi
Hardness, Shore D (24 hours, 5 days)	ASTM D2040	70, 86
Taber Abrasion (CS-17 Wheel, 1000 mg. Load, 1000 Cycles)	ASTM D4060	30 mg Loss
Tensile Strength	ASTM D638	9,600 psi
Gloss @ 60 Angle	ASTM D523	92 – 95
UV Resistance (gloss after 1000 hours in QUV)	ASTM G154	87 – 89
VOC	EPA Method 24	< 50 g/L

CHEMICAL RESISTANCE

CHEMICAL	RESULTS	CHEMICAL	RESULTS	CHEMICAL	RESULTS
10% Acetic Acid	F	Methyl Ethyl Ketone	G	Betadine	G*
Vinegar	F	Xylene	F	Bleach	E
10% Citric Acid	E	Ethylene Glycol	E	Urine	E
10% Hydrochloric Acid	E	Isopropyl Alcohol	E	Coffee	E
30% Hydrochloric Acid (muriatic)	E	Mineral Spirits	E	Cola	E
10% Nitric Acid	NR	Brake Fluid	NR	Ketchup	F
50% Phosphoric Acid	NR	Transmission Fluid	E	Mustard	F
10% Sulfuric Acid	E	Motor Oil	E	Red Wine	E
37% Sulfuric Acid	G	50: 1 Gas/Oil Mixture	E		
70% Sulfuric Acid	NR	E85 Gasoline	E		
20% Ammonium Nitrate	E	E95 Gasoline	E		
20% Sodium Chloride	E	Unleaded Gasoline	E		
50% Sodium Hydroxide	G	Skydrol	E		

*Stain is only defect.

KEY	
E = Excellent	G = Good
F = Fair	NR = Not Recommend

SURFACE PREPARATION

Concrete and coated concrete surfaces must be sound, clean, dry, and free of contaminants such as loose coatings, dirt, dust, grease, oil, silicone, and other contaminants that may negatively affect adhesion.

MOISTURE VAPOR BARRIER: A suitable moisture barrier must be in place for concrete slabs on-grade. If a moisture barrier is not in place, seasonal variations in ground moisture can cause excessive moisture vapor transmission (MVT) regardless of results measured prior to coating application. MVT rate must not exceed three pounds per 1,000 square feet per 24 hours, as directed by ASTM F1869. The relative humidity (RH) of the slab must not exceed 75%, as directed by ASTM F2170. If there is a moisture situation in excess of the above rate, the use of Simiron MVB Moisture Vapor Barrier Primer may be required. Consult a Simiron Representative for details and application procedures.

NEW/BARE CONCRETE: Diamond grind or shotblast to a CSP-3 or greater surface profile. Refer to SSPC-SP13 / NACE 6 or ICRI Technical Guideline No. 310.2. New concrete must be cured a minimum of 28 days and should meet moisture vapor transmission (MVT) and relative humidity (RH) thresholds as described above.

SURFACE PREPARATION (CONT.)

PREVIOUSLY COATED SURFACES: Clean surface to prevent any contaminants from being spread/redistributed to a greater area being prepared. Thoroughly grind the surface with 30 grit metal diamonds to completely remove any grout or topcoats that are not epoxy based and provide proper surface profile required for adhesion of the system.

SAFETY & TECHNICAL

Refer to the SDS sheet before use. Safety precautions must be strictly followed during storage, handling, and use. Personal Protective Equipment (PPE) should be worn at all times. PPE will include (but is not limited to): Safety glasses with side shields, high-quality nitrile gloves, and properly fitted NIOSH approved respirators. To acquire additional information or technical and safety data, please visit: www.simiron.com.

TEMPERATURE

Air	55° - 85°F	12.8° - 29°F
Surface	55° - 85°F	12.8° - 29°F
Material	55° - 85°F	12.8° - 29°F

Higher temperatures and humidity will shorten pot-life and working time.

SET-UP & MIXING AREA

Place the mixing area as close to the project area as possible. Cover mix area with plastic, a tarp, or cardboard and securely tape to the floor. Assemble all necessary application tools, safety supplies & PPE, and clean-up supplies and place in the mixing area prior to starting the application process.

TAPE AND TERMINATION POINTS: Apply masking tape to all perimeter areas where the coating system will terminate. Sawcut and key-in all termination points around drains, dock plates, and high traffic impact points (see Simiron Drawings/Architectural Details).

PATCHING

Cracks, holes, eroded & spalled areas of the floor should be patched with Simiron 800CF Epoxy Crack Filler or a Simiron 100% Solids Epoxy thickened with fumed silica. For best results, scrape patch material flush with the surface. After priming, check to see if additional patching is required.

JOINTS

Honor all isolation, expansion, and movable joints with the appropriate joint material after the coating system is installed. Contraction (sawcut) joints may be filled and coated over; However, the coating system may crack over time if the slab experiences excessive shrinkage or movement (see Simiron Drawings/Architectural Details).

APPLICATION EQUIPMENT

Assemble all required application equipment. Equipment will include (but is not limited to):

- Drill and Jiffy® type mixing blade
- High quality non-shed 3/8" nap roller covers
- Edge rollers & chip brushes
- Painters' tape
- Duct tape
- High quality flat & notched EPDM squeegees
- Flat metal spring blade squeegee
- Spiked shoes
- Roller pans
- Measuring and mixing containers

APPLICATION PROCEDURE

1000HS Primer:

1000HS Primer mix ratio is 2 Parts Base to 1 Part Activator by volume.

1. Pre-mix Base at low speed for 1 minute. Add Activator and mix for three minutes until uniform. Do not mix more material than can be applied in 10 – 15 minutes (material will stiffen or tack-up).
2. Immediately pour mixed 1000HS Primer on the floor in a long bead approximately 8 – 12 inches wide.
3. Wearing spiked shoes, spread evenly at 3 – 8 mils by pushing a flat squeegee or metal spring blade along the bead. Overlap previous passes in order to ensure concrete pinholes are filled. A tight, thin coat of primer with no back-roll is the best way to minimize outgassing bubbles.
4. If back-rolling, use a non-shed 3/8" roller and back-roll the primer evenly across the squeegee passes to minimize application lines and leave a consistent film thickness.
5. After the 1000HS Primer has dried (see 1000HS data sheet for drying schedule), apply the 1100SL basecoat and vinyl chip broadcast.

1100SL 100% SOLIDS SELF LEVELING EPOXY: Broadcast

1100SL 100% Solids Self Leveling Epoxy mix ratio is 2 Parts Base to 1 Part Activator by volume. 1100SL is a clear base that may be pigmented with 1 pint of Simiron E-Tint per 3 gallons of 1100SL. Since it is unlikely to completely cover the epoxy with a single broadcast, it is recommended to tint the epoxy with a similar color in the blend of DECORATIVE CHIP. For example, for a predominantly gray blend of decorative chip, use a gray color of 1100SL.

1. Pre-mix Base at low speed for 1 minute. Add Part B and mix for three minutes until uniform. Do not mix more material than can be applied in 10 – 15 minutes (material will stiffen or tack-up.)
2. Immediately pour mixed 1100SL on the floor in a long bead approximately 8 – 12 inches wide.
3. Wearing spiked shoes, spread evenly at 8 – 12 mils by pushing a 1/8" notched squeegee along the bead. Overlap previous passes in order to ensure consistent coverage.
4. Push the squeegee with a slight angle to plow extra material to the side, moving it down the floor.
5. Using a non-shed 3/8" roller, back-roll the 1100SL evenly across the squeegee passes to minimize application lines and leave a consistent film thickness.
6. Allow 10 – 15 minutes for the 1100SL to level and broadcast the vinyl chip into the wet coating at the rate of 6 sq. ft. per lb. or 300 sq. ft. per 50 lb. box of DECORATIVE CHIP. Use caution to avoid walking in the chip after it has been broadcast onto the floor. Always leave a wet edge or a thin strip of 1100SL without a chip broadcast to blend in different mixes of 1100SL with the roller cover.
Do not dump or allow DECORATIVE CHIP to pile on the floor.
7. After the 1100SL has dried (see 1100SL data sheet for drying schedule), vacuum excess vinyl flakes from the floor. Being careful not to damage the coating or the chips, gently scrape the floor with a floor scraper to remove any loosely bonded chip.

POLYASPARTIC HS SLOW CURE: Topcoat

Slow Cure mix ratio is 1 Part Base to 1 Part Activator by volume.

Pre-mix Part A for 1 minute. Add Part B and mix for three minutes until uniform. Do not mix more material than can be applied in 10 – 15 minutes (material will stiffen or tack-up). Mix full kits only.

8. Using a flat or notched rubber squeegee (depending upon DFT required) with EPDM rubber blade, apply at a spread rate of 100 – 160 sq. ft. per gal. to yield 10 – 16 wet film thickness. Use a non-shed 3/8" roller for back-rolling.
9. In hot or humid conditions, apply via 18" roller in a dip and roll method from a roller pan as increased heat and humidity will decrease the working time of the material.
10. This material will cure faster with exposure to moisture in the air.
11. To avoid visible differences in texture or mix-to-mix "tie-ins" do not exceed 5 – 10 minutes from one mix to another.
12. Use joints as natural breaks to divide sections of the floor.
13. If less texture is desired, apply a second coating of 6 – 8 mils (no more than 200 sq. ft. per gal.) on top of the previous coat within 24 hours.

Applying thicker than recommended, allowing material to pool, or rolling into late may leave a white, hazy appearance.

CLEAN UP & DISPOSAL

Clean up mixing and application equipment immediately after use. Use acetone, or xylene; do not use alcohol. Follow solvent manufacturer's safety instructions. Be sure to follow all local, state, and federal regulations when disposing of materials.

MAINTENANCE

To maintain the appearance and extend the life of the newly sealed surface, it is imperative to have a routine maintenance program. Dirt and debris that is tracked over a finished floor will quickly scratch and dull the surface. Place walk-off mats at entrances. Sweep and mop/scrub floors regularly using soft bristles/pads and a mild cleaner. Some cleaning products and equipment or improper use of these can damage a surface. Remove spills quickly to minimize damage and/or stains. For systems that support parked vehicles or other heavy items on rubber wheels, place a small piece of nonporous material, such as sheet metal or plexiglass between the tires and floor to prevent tire marks. Reapplication may be necessary in heavy traffic areas.

LIMITATIONS

⚠ Do not apply at temperatures or thicknesses not recommended. Do not delay in pouring mixed material onto the floor. Do not make partial mixes. Do not invert epoxy pails to drain. Do not apply over loose or unsound concrete, asphalt or bitumen substrates, glazed tile or nonporous brick and tile, magnesite, copper, metal, polyesters, or elastomeric membranes. Moving joints and shrinkage cracks may reflect through system. Joints that are designed to move may reflect through the finished flooring system if they are not honored. Tire marking may occur.

SHELF LIFE & STORAGE

12 months for unopened containers when stored indoors at 55°F – 85°F (13°C – 29°C) in a dry location.

⚠ Do not allow materials to freeze.

Shelf life of 12 months from the date of manufacture on the label in the original unopened container stored in recommended conditions.

LIMITED WARRANTY

SIMIRON warrants this product to be free from defect in the material that affects its performance for a period of one year (from date of purchase). SIMIRON will replace at no charge the quantity of the coating that SIMIRON determines has failed to perform, as the sole and exclusive remedy for any breach of this warranty and/or any other defect or failure of the coating. Proof of purchase is required. Cost of labor for application of any product specifically is excluded. Warranty is void if Simiron products are mixed with or used in conjunction with materials that are substituted for Simiron products. Warranty is nontransferable.

TECHNICAL ASSISTANCE



Information is available by calling SIMIRON
Toll Free: 1.866.515.8775 / +1.248.686.3600



CORPORATE OFFICE:

Simiron Inc.
3000 Research Drive
Rochester Hills, MI 48309-3580
(248) 686-3600 / (866) 515-8775

SYSTEM GUIDE: 8/2022

Disclaimer: All information provided by Simiron, Inc. concerning Simiron products, including but not limited to, any recommendations and advice relating to the application and use of Simiron products, is given in good faith based on Simiron's current experience and knowledge of its products when properly stored, handled, and applied under normal conditions in accordance with Simiron's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual conditions and other factors outside of Simiron's control are such that Simiron assumes no liability for the provision of such information, advice, recommendations or instructions related to its products. The uses of Simiron product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s).

Simiron reserves the right to change the properties of its products without notice. All Simiron product(s) are subject to its current terms and conditions of sale which are available by calling (866) 515-8775.